



tradition • innovation • quality

DO-IT-YOURSELF


a.b.e.® Construction Chemicals

silvakote eco

HIGH PERFORMANCE UV REFLECTIVE ALUMINIUM COATING



CONCRETE SURFACES



METAL SURFACES



BITUMEN & GALVANISED SURFACES

WATERPROOFING

DESCRIPTION

silvakote eco is a liquid applied, high performance, highly elastomeric, solar reflective finishing coat modified with synthetic polymers. **silvakote eco** is both bitumen and solvent free. Being water based, **silvakote eco** is environmentally and applicator friendly, and is designed to act as a green replacement for traditional solvated bitumen based aluminium paints.

USES

- Exposed concrete and metal roofs.
- Bitumen felt reflective top coat (new build).
- Bitumen felt top coat (refurbishment).
- Polymer modified bitumen waterproofing membrane reflective top coat.
- Liquid applied bitumen systems reflective top coat.

ADVANTAGES

- Brilliant aluminium finish every time, with no streaking.
- Excellent solar reflectance, protecting both liquid and felt systems.
- Eliminates "cracking or crazing" problems associated with traditional solvated aluminium paints, as the product is elastomeric.
- Non-hazardous for transport and storage.
- Non-flammable, eliminates site health & safety issues.
- Solvent free – no bleed through from previous coating systems.
- Good resistance to light foot traffic.

COLOUR



- Minimal mixing required prior to application.
- Bitumen free – no chance of "bronzing" due to low aluminium flake.

PROPERTIES

Appearance	Bright Aluminium Liquid
Specific Gravity	0.98
Flash Point	Not applicable
TSR	>50%
Resistance to UV	Excellent
Application Temp	+5 °C to +55 °C
Drying Time	Touch Dry – approximately 30 minutes @ 20 °C Full Cure – approximately 2 hours @ 20 °C
Coverage Rate	8 m ² to 10m ² per liter depending on substrate porosity

CONDITIONING OF NEW BITUMINOUS SURFACES

Newly applied polymer modified bitumen membranes or bituminous coatings - either hot or cold applied - should not be treated with reflective or protective liquid coatings until at least two months after application. In particular, newly applied polymer modified bituminous membranes acquire superficial "efflorescence of hydrocarbons" which prevents optimum adhesion of coatings. The ageing period will depend on seasonal conditions and on the heat of the sun which encourages drying out and superficial oxidation of the polymer bitumen and the elimination of the Hydrocarbon substances that prevents adhesion of coatings. If in doubt about the condition of the bitumen surface, it will be necessary to test the adhesion of **silvakote eco**.

PREPARATION OF OLD BITUMINOUS SURFACES

Particular care must be taken to prepare old bituminous coatings. Any superficial bubbles should be cut and then resealed having first made certain that all traces of moisture and dampness have been removed.

PRIMING & GENERAL SURFACE PREPARATION

Any surface to be coated should be clean and mechanically sound.

CONDITIONED BITUMEN SURFACES

Ageing of the bitumen yields considerable quantity of water soluble dust derived from the oxidization process of the bitumen surface. This water soluble dust must be washed off the immediate surface by scrubbing and using copious quantity of clean water. No priming is required.

OTHER TYPICALLY COATED SURFACES

Fungus contaminated porous surfaces are particularly common in areas of high humidity; coating over fungus will always give rise to problems. The following pre-treatment will usually prove successful:

- Scrub the surfaces with detergent and water (high pressure washing is recommended).
- Flush the surface thoroughly to remove all detergent and residues.
- Wash the surface with a proprietary hypochlorite bleach to remove all fungal stains.
- Wash with a fungicidal solution such as a 10% solution of Detol or equivalent to minimise re-infection.
- Allow the surface to dry.
- Apply the primer coat.

For further information on Surface Preparation, see data sheet "Preparation of Surfaces" When preparing and cleaning on fiber cement sheets refer to Everite Building Products and Asbestos Regulation (2001). Concrete, Cement roofing tiles and fiber cement sheeting should be free from dust, laitance and any loose or friable existing coatings. These surfaces should be primed with a coat of **dura.® proof acrylic primer** thinned 1:1 with clean water. Alternatively on fiber cement sheets, **dura.® coat WB Primer** can be used as a primer.

Galvanised iron sheeting should be free of dust and any flaking existing coating and be corrosion free. Previously uncoated galvanized sheeting should be free of any traces of passivation (corrosion resistant treatment). If present this should be completely removed by means of an abrasive pad or propriety abrasive cleaner to a water break-free surface indicating thorough cleaning. Galvanized metal should be primed with **4 metal primer**.

APPLICATION

silvakote eco is applied by brush, roller, or airless spray, and adheres well to all common building substrates such as concrete, steel, bitumen felt, most plastics, polystyrene, and polyurethane foams. Do not apply **silvakote eco** if rain, fog or temperatures under 5 °C are expected. These conditions should be ensured for at least 6 hours after application of the product.

Film Thickness: Where relevant, at least one wet film thickness measurement shall be taken for every 5 m² installed.

Consumption: Daily completed areas should be measured against quantities of materials used, to ensure correct coverage.

LIMITATIONS

silvakote eco is not for use in ponded areas.

Provide proper falls in concrete: The finished roof should have a slope of at least one in 80. This is in order to prevent prolonged water stagnation over the **silvakote eco** film.

STORAGE

Store in a cool dry area; cans must always be stored at 5 °C or above to ensure product is suitable for use when opened. Cans must be kept closed and the product must not be allowed to freeze.

SHELF LIFE

12 months when stored as recommended.

MODEL SPECIFICATION

A bitumen and solvent free aluminium paint for metallic, concrete and waterproofed surfaces. The aluminium paint will be **silvakote eco**, a one component, aluminium reflective coating applied in accordance with the recommendations of **a.b.e.® Construction Chemicals**.

HEALTH & SAFETY

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The safety data sheet is available from your local **a.b.e.® Construction Chemicals** branch.

