

Technical data sheet

CHRYSO® Dem Oleo FW

Release agent - Hydrocarbon oil based,
for conventional jobsites

Description

CHRYSO®Dem Oleo FW is a Hydrocarbon based, recycled delayed release agent for all types of formwork on conventional jobsites only. Not suitable for precast.

Advantages

- Ideal for formwork suppliers
- Easy formwork release - temporarily protects and extends the life of metallic formwork from corrosion
- Ready to use - reduces the likelihood of errors that can occur if dilution is required
- Reduces the likelihood of imperfections and surface damage (particularly blow holes) to the concrete, creating more durable, blemish free and consistent concrete surfaces
- Does not affect the adhesion of subsequent finishes and coatings. Plaster, paint and other coatings may be applied subsequently
- Does not stain or affect the colour of the concrete, when applied correctly
- Does not modify cement hydration when applied correctly
- Water repellent and not affected by rain

Application guidelines

Use

Suitable for all types of formwork including:

- Metal (steel/aluminium)
- Wood (timber/plywood/resin ply/shutter board)
- Plastic
- Rubber
- Latex
- Polyurethane

Physical and chemical properties

- Physical state (@ 25 °C): liquid
- Colour: amber
- Specific gravity (@ 25 °C): 0.850 - 0.880
- pH: 6.0 - 7.0
- Viscosity: 10 - 15 secs (Ford # 4 cup)

- Polystyrene
- Fibreglass
- Other

Directions


Before application

- The formwork must be stripped and cleaned of hardened concrete residue, dust, dirt, rust, oil deposits and any form of deleterious substance.
- CHRYSO®Environmentally Friendly Cleaning Agents will facilitate the cleaning process

- CHRYSO®Dem Oleo FW should be applied to the formwork prior to erection of formwork, the fixing of reinforcement and as near as possible to the first concrete pour

After application

- The formwork should be re-coated if casting is scheduled more than 2 days after CHRYSO®Dem Oleo FW has been applied
- In the event of exposure to dust and dirt, the formwork must be stripped and cleaned. CHRYSO®Dem Oleo FW must then be re- applied
- After the formwork has been used, it should be cleaned and CHRYSO®Dem Oleo FW should be applied immediately to protect it from rust



Technical data sheet

CHRYSO® Dem Oleo FW

Release agent - Hydrocarbon oil based,
for conventional jobsites

■ Coverage

- CHRYSO®Dem Oleo FW needs to be applied as thinly as possible to the entire formwork surface, by means of an appropriate pressure spray, paintbrush or roller
- Metallic/plastic formwork: 45 m²/1 ℓ
- Wooden formwork: 25 - 35 m²/ 1 ℓ

Precautions

- Avoid insufficient or excessive application. Too much is just as bad as too little
- Avoid the accumulation of excessive dust/dirt on the surface of the formwork
- Not suitable for precast concrete

Storage

- If in the original sealed packaging, CHRYSO®Dem Oleo FW has a shelf life of up to 24 months from the date of manufacturing
- Avoid storing CHRYSO®Dem Oleo FW in direct sunlight
- In its stored state, CHRYSO®Dem Oleo FW should not come into direct contact with water or rain.
- Should the product freeze, it will recover its properties after thawing and agitating

Packaging

- 25 ℓ jerry can
- 200 ℓ drum
- 1000 ℓ flow bin
- Delivery on request

Health and safety

- CHRYSO®Dem Oleo FW is classified as combustible.
- CHRYSO will provide onsite assistance when requested.
- For more information refer to the material safety data sheet.

The information contained in this document is given to the best of CHRYSO's knowledge and is the result of extensive testing. However, this document will not under any circumstances be considered as a warranty involving CHRYSO's liability in case of misuse. Tests should be carried out before any use of the product to ensure that the methods and conditions of use of the product are satisfactory. CHRYSO specialists are at the disposal of the users in order to help them with any problems encountered.