




tradition • innovation • quality

a.b.e.® Construction Chemicals

super laycryn

DO-IT-YOURSELF


PROFESSIONAL LIQUID WATERPROOFING COMPOUND



Roof laps



Flashings



Roof screws

WATERPROOFING

DESCRIPTION

super laycryn is a highly flexible liquid applied emulsion reinforced with **abe® membrane** to provide an in situ, seamless professional waterproofing system.

USES

super laycryn is recommended for:

- All types of flashings.
- Parapet walls.
- Flat roof waterproofing.
- Re-waterproofing over existing waterproofing systems.
- Sealing of joints, laps and roofing screws on corrugated roofs.
- The system is for non-trafficable roofs.

ADVANTAGES

- **super laycryn** is an all-in-one system.
- There is no need for separate primers (apart from metal surfaces) or top coats.
- It has excellent weathering properties, adhesion and is tough, flexible and non-toxic.
- It comes in a wide range of colours.
- 10-year product quality guarantee.

COLOUR



SURFACE PREPARATION

All surfaces to be clean, dry, sound and free of all laitance, grease, oil or loose and flaking particles.

BONDING/PRIMING

All surfaces (except metal) – Mix 1 part **super laycryn** with 1 part clean water and prime total area to be covered. As a guide, 0.1 L of **super laycryn** mixed with 0.1 L of water will prime an area of 0.75 m².

Allow to dry for ± 30 minutes.

Metal surfaces only – Prime with **4-metal primer**. This not only gives excellent adhesion but resists rust. Allow to dry for 4 hours. **Note:** Do not use solvent based bituminous solutions as a primer.

TYPICAL PHYSICAL PROPERTIES

Density (typical)	1.18 g/cm ³
Flash point	None
Finish	Matt
Fire resistance of wet film	Non-flammable
Consistency	Soft thixotropic
Available colours	Red, grey, charcoal, burgundy, white, green and terracotta
Drying time @ 25 °C	Touch dry: 1 hour Hard dry: 24 hours Full cure: 7 days

MIXING

Stir well before use.

COVERAGE

2.1 L/m² for total system.

APPLICATION

First coat (all surfaces after priming) – Brush or roll on a fairly thick coat of **super laycryn** (1 L/m²). Bed the membrane into the wet coat by using a roller or a stiff brush, avoiding the formation of bubbles or wrinkles. On flat surfaces it is recommended to use a fluted aluminium roller. Membrane overlaps should be a minimum of 100 mm on end laps and 75 mm on side laps.

Second coat – Once the first coat has dried sufficiently to take working traffic (2 – 3 hours depending upon weather), apply a second coat of **super laycryl** (0.5 L/m²) to ensure the membrane is completely saturated.

Third and final coat – When the second coat is dry, apply a finishing coat of **super laycryl** at right angles to the second coat (0.5 L/m²).

CLEANING

Tools, brushes and mixing equipment should be cleaned immediately after use and before material has set with **abe**® **super brush cleaner** followed by washing with soap and water.

PROTECTION ON COMPLETION

Whilst **super laycryl** is designed for an extended life, it is important to apply a maintenance coat (**super laycryl**) every 2 to 3 years to validate the product warrantee.

Note: Do not cover with stones or stone chippings

TEMPERATURE AND RELATIVE HUMIDITY

Do not apply **super laycryl** if rain is imminent or if the temperature is below 5 °C.

MODEL SPECIFICATION

Coloured acrylic and rubberised bitumen waterproofing flashing system plus **abe**® **membrane**. The waterproofing/flashing system will be **super laycryl**, a single pack, elastic acrylic and rubberised bitumen compound applied in accordance with the recommendations of **a.b.e.® Construction Chemicals**, including **abe**® **membrane** and **4-metal primer** where necessary.

PACKAGING

1 L, 5 L, 20 L containers.

HANDLING AND STORAGE

This product has a shelf-life of 12 months if kept in a dry cool place in the original packaging. In more extreme conditions this period might be shortened.

HEALTH AND SAFETY

super laycryl is non-flammable but should not be allowed contact with skin and eyes. The use of gloves and eye protection is advised. Splashes into eyes should be washed immediately with plenty of clean water and medical advice sought thereafter. Cured **super laycryl** is inert and harmless.

IMPORTANT NOTE

This datasheet is issued as a guide to the use of the product(s) concerned. Whilst **a.b.e.® Construction Chemicals** endeavours to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot – because **a.b.e.®** has no direct or continuous control over where and how **a.b.e.®** products are applied – accept any liability either directly or indirectly arising from the use of **a.b.e.®** products, whether or not in accordance with any advice, specification, recommendation, or information given by the company.

FURTHER INFORMATION

Where other products are to be used in conjunction with this material, the relevant technical datasheets should be consulted to determine total requirements. **a.b.e.® Construction Chemicals** has a wealth of technical and practical experience built-up over years in the company's pursuit of excellence in building and construction technology.

DATE UPDATED: 22/01/2020

a.b.e.® is an ISO 9001:2015 registered company
Registration Number: 1982/005383/07
101 Main Reef Road, Boksburg North, 1459
PO Box 5100, Boksburg North, 1461

a.b.e.® Construction Chemicals (Pty) Ltd
is a CHRYSO Group Company

CHRYSO